Jaeger zinc repair spray 497

Repairs minor damage to hot-dip galvanized steel

Material description

Material type: Repair spray based on acrylic resin for indoors and outdoors

Intended use: Jaeger zinc repair spray 497 is the quick solution for repairing small damaged areas on hot-dip galvanized steel. Use on e.g. tubs, garden gates, gutters, crash barriers, drainpipes, containers and much more.

Properties:

- Quick drying
- weather resistant
- good coverage
- lightfast
- scratch resistant
- Very good adhesion
- Resistant to gasoline

Color shades:

Order no:	**Color shade:**
497-0000	silver

Packaging: 3 x 400 ml spray can

Storage: Store in a cool and dry place. Official regulations must be observed.

Technical application notes

Substrates: Hot-dip galvanized steel.

Substrate preparation: The substrate must be clean and dry.

Processing conditions: Bring spray can to room temperature of approx. 20°C - 22°C. Shake well before use, apply in several thin coats at intervals of 25 cm. Shake again and again between sprays to prevent the pigments from settling.

After use, turn can upside down and spray valve empty. Cover parts not to be painted beforehand. For small areas, make a cardboard template and place it on the surface beforehand.

During the entire processing and drying time, the material, substrate and air temperature must not fall below 8°C and not exceed 30°C. The air humidity should be between 30% RH and 75% RH during the entire time. Only apply in dry weather and in areas protected from the wind.

Labeling

Disposal: Only dispose of completely empty containers for recycling.

Other: The accident prevention regulations of BG Chemie "Processing of coating materials" (VBG 23), the leaflet "Solvents" (M 017) and the "Technical Rules for Hazardous Substances (TRGS) 507" must be observed.

Remove food from the relevant rooms during processing and the drying time.

Further information can be found in the EC safety data sheet.

Processing instructions

Drying / recoatability	Dust-dry	non-slip	paintable
(20°C/55% r.h.) *	~ 10 min	~ 20 min	~ 2 min
Yield m² / can	~ 1,5		

Special notes

Drying times can also vary depending on the temperature, climate and applied layer thickness.

* Specified drying times apply at 20°C / 55% relative humidity and sufficient air movement.
The following conditions may delay drying:

- Low temperatures
- High humidity
- Excessive layer thickness
- Lack of air movement

Status 11/14
PAUL JAEGER GMBH & CO. KG• Siemensstrasse 6• 71696 Möglingen• Phone +49 7141-24 44-0• Fax +49 7141-24 44 55• info@jaegerlacke.de •www.jaegerlacke.de
Our written and verbal application recommendations, which we provide to support the processor on the basis of our practical experience and to the best of our knowledge in accordance with the current state of science and technology, are non-binding and do not constitute a contractual legal relationship or an ancillary obligation arising from the purchase contract. They do not release the purchaser from the obligation to check the suitability of the products for the intended purpose on his own responsibility. In the event of the publication of a new edition due to technical progress, the above information shall lose its validity. In all other respects, our General Terms and Conditions apply.