Jaeger Stucco Fondo 960

Mineral base filler for smoothing and marbling techniques indoors

Material description

Material type:	Mineral-bonded lime-granite mixture for interior use.
Intended use:	As a fine filler for substrate preparation for particularly high-quality smoothing and marbling techniques in interior areas, especially for Jaeger Stucco Veneziano and other high-quality painting techniques.
Properties:	• good filling • Easy to sand • Water vapor diffusible • environmentally friendly • does not tear • incombustible
Color shades:	**Order no**: 960 0000 — **Color shade:** white
Density:	approx. 1.6 g / cm^3 at 20°C
Packaging:	5 kg — 25 kg
Dilution:	adjusted ready for use
Yield:	Depending on layer thickness per layer approx. 0.4 kg / m^2
Storage:	Store in a cool, dry place in a tightly closed original container. Official regulations must be observed. Protect from frost!

Technical application notes

Substrate preparation:	First consolidate the substrate with Kronen® Hydrosol Tiefgrund 307. If necessary, prime with Jaeger Iso-Mineralgrund 309. Priming with Jaeger Iso-Mineralgrund improves adhesion and facilitates the application of Jaeger Stucco Fondo. Before applying Jaeger Stucco Fondo, the surface can also be lightly sanded (sandpaper P 80 - 100).
Working method:	Jaeger Stucco Fondo is applied in several thin coats with the Jaeger smoothing trowel or the Jaeger Veneziano spatula until completely smooth, then sand dry with P 320 grit sandpaper depending on the roughness.
Drying time:	approx. 1 - 5 hours, depending on layer thickness and temperature.
Processing conditions:	During the entire processing and drying time, the material, substrate and air temperature must not fall below 8°C and not exceed 30°C. The air humidity should be between 30% RH and 75% RH during the entire time.
Tool cleaning:	Clean with water immediately after use.

Labeling

Declaration of ingredients:	Mineral fillers, polymer emulsion, wetting and dispersing agents		
Waste code:	080112	**Giscode:**	No classification
Disposal:	Only dispose of completely empty containers for recycling. Hardened residues can be disposed of with the residual waste. Liquid paint residues must be disposed of via the hazardous waste collection points or approved disposal companies.		
Other:	The accident prevention regulations of BG Chemie "Processing of coating materials (VBG 23), the leaflet "Solvents" (M 017) and the "Technical Rules for Hazardous Substances (TRGS) 507" must be observed. Remove food from the relevant rooms during processing and the drying time. Further information can be found in the EC safety data sheet.		

Status 11/14
PAUL JAEGER GMBH & CO. KG• Siemensstrasse 6• 71696 Möglingen• Phone +49 7141-24 44-0• Fax +49 7141-24 44 55• info@jaegerlacke.de •www.jaegerlacke.de
Our written and verbal application recommendations, which we provide to support the processor on the basis of our practical experience and to the best of our knowledge in accordance with the current state of science and technology, are non-binding and do not constitute a contractual legal relationship or an ancillary obligation arising from the purchase contract. They do not release the purchaser from the obligation to test products for their suitability for the intended purpose on his own responsibility. In the event of the publication of a new edition due to technical progress, the above information shall lose its validity. Otherwise, our General Terms and Conditions apply.